



The
Thermoclad
Company

► ► ► ► ► ► ► ► Technical Data Sheet

DURATOP ACW
Flat Black Acrylic
W-1300 Series
Technical Data Sheet

DURATOP ACW, is an economical modified acrylic blend especially designed for conventional spray, flow, dip or brush air dry finish operations. It offers benefits of energy conservation and higher application solids to comply with increasing governmental restrictions on solvent emissions, flammability and hazardous ingredients.

Suggested Uses:

General industrial coating for Metal Equipment, Cabinets, Castings, Hardware, Lawn and Garden Equipment, Appliances, Lighting Fixtures and **Carbon Composites**.

Properties

Appearance	Black Liquid
Non Volatile % By Weight	>32.19
VOC Level Lbs./Gallon	<2.50
Viscosity #2 Zahn @ 77°F	24 Seconds
Weight Per Gallon	8.69 ± 0.25
Theoretical Coverage Ft ² /gallon	530 @ 1 mil DFT 1060 @ 0.5 mil DFT

Properties After Cure

60° Gloss	10 ± 3
Pencil Hardness	HB+
Color Retention	Excellent
Gloss Retention	Excellent
Chemical Resistance	Very Good
Salt Spray	200+ Hours
Heat Aging at 400°F	Very Good

Cure Schedule

Air dry or force air dry up to 200°F. Will dry in less than 5 minutes @ 130°F at 0.50 mills Dry Film Thickness.

The above properties of DURAVIN or DURATOP products are based upon tests and data believed to be reliable, since actual use by others is beyond our control, no guarantee, expressed or implied, is made by Thermoclad Company as to the effects of such use or results to be obtained.

Corporate Office ▼ 361 West 11th Street ▼ Erie, PA 16501-1703 ▼ PH 814.456.1243 ▼ FX 814.459.2853

E-mail info@thermoclad.com / www.thermoclad.com

The above properties of DURAVIN or DURATOP products are based upon tests and data believed to be reliable, since actual use by others is beyond our control, no guarantee, expressed or implied, is made by The Thermoclad Company as to the effects of such use or results to be obtained.